Data sheet: HPUGR01 Revised: 30/1/2020



## **HPU premium green**

## Hydrolyses resistant Polyurethane

Standard Colour: Green

- Resistant against mineral oil, HFD-U and HETG = biological base, acid oils and gases, cold water and diluted acids and bases
- Applicable for Rod and Piston seals, Wiper seals, Rotary seals and Static seals.

Properties	Unit	Din Standard	Value
Hardness	Shore A	DIN53505	94 ± 3
Hardness	Shore D	DIN53505	$49 \pm 3$
Density	g/cm <sup>3</sup>	DIN EN ISO 1183-1	1.21
Compression set 70°C/24h	%	DIN ISO 815-1	20
Compression set 70°C/70h	%	DIN ISO 815-1	22
Compression set 100°C/24h	%	DIN ISO 815-1	27
Elongation at break	%	DIN53504	382
100% modulus	N/mm <sup>2</sup>	DIN53504	15.3
300% modulus	N/mm <sup>2</sup>	DIN53504	44.5
Rebound resilience	%	DIN53512	39
Tear strength	N/mm	DIN53515	40.1
Min. service temperature	°C		-30
Max. service temperature short	°C		+125
Max. service temperature constant	°C		+110

All above stated data results from random tests which were taken from the ongoing production. All data was established based on standard test-products according to ISO, DIN and ASTM standards and can basically not be carried over to the completed seal.